

Isocrete PP Fibres

Description

High performance crimped monofilament 12 mm long polypropylene fibres.

Uses

To improve the durability of cementitious screeds and toppings by inhibiting the formation of small cracks, which occur because of plastic shrinkage and settlement due to premature drying.

Durability is further enhanced due to increased residual strength, resulting in improved abrasion, impact and spalling resistance.

Even distribution throughout the mix is due to fibres being coated with a special dispersing agent. Improves fibre bond and eliminates the requirement for shrinkage control wire mesh reinforcement.

Isocrete PP Fibres are intended for use in the Isocrete products K-Screed, Fast-K, Screedfast, Isogran, Isopol SBR and other polymer modified and conventional cementitious screeds and toppings.

Please note that Isocrete PP Fibres **cannot** be used as a replacement for structural steel reinforcement.

Benefits

- Inhibits plastic shrinkage and settlement cracking
- Eliminates shrinkage control wire reinforcement
- Cost effective compared with wire reinforcement
- Specially pre-bagged to ensure correct dosing
- Improved abrasion, frost and impact resistance (good drop hammer results)
- Over 300 million fibres per m³ of screed
- Controlled dispersion throughout the mix
- Reduced permeability and water absorption
- Reduced segregation and bleeding
- Improves surface finishing
- Alkali resistant and will not corrode
- BBA approved product (Cert. No 92/2830)

Model Specifications

Product: Isocrete PP Fibres

Isocrete PP Fibres (polypropylene fibre reinforcement) dosed at 75 g per 25 kg cement.

Preparatory work and application in accordance with the manufacturer's instructions.

Manufacturer: Flowcrete UK Ltd

Telephone: Customer Service - +44 (0) 1270 753000

Products Included in this System

For use in the Isocrete products K-Screed, Fast-K, Screedfast, Isogran, Isopol SBR and other polymer modified and conventional cementitious screeds and toppings.

Detailed application instructions are available upon request.

Installation Service

Several of the Isocrete proprietary screeds should only be installed by a Flowcrete approved licensee in accordance with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our web site www.flowcrete.com

The installation of conventional systems can be performed by any competent contractor.

Typical Mix Designs

Isocrete PP Fibres may be used in any cement based screed at a dosage of 75g per 25kg cement, 150g per 50kg cement or 500g per tonne of ready mixed screed (i.e. approx 1 kg per cubic metre). Examples of typical mix designs for Isocrete proprietary screeds can be obtained from our Technical Advisors.

Focus on the Floorzone

Flowcrete Group plc are world leaders in specialist industrial and commercial flooring. Systems available include: underfloor heating systems, floor screeds, surface damp proof membranes, decorative floor finishes, seamless terrazzo, car park deck waterproofing, tank lining systems... to name just a few.

Our objective is to satisfy your Floorzone needs.

Important Note

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

Screed Reinforcement

Unbonded and floating screeds require continuous reinforcement to control shrinkage cracking.

This can be difficult to achieve using D49 fabric reinforcement in faster setting systems such as Isocrete Screedfast and Isocrete Fast-K.

Bonded screeds and toppings in excess of 70 mm thick also benefit from continuous reinforcement to control plastic drying shrinkage. Isocrete PP Fibres dispersed fully throughout the screed mix effectively minimise the risk of such cracking and crazing due to shrinkage.

At day joints, steel fabric to BS 4483 Ref D49 should be provided as additional reinforcement, nominally at the centre of the screed.

Curing

Normal good curing practices for conventional screeds or toppings must be strictly followed. It is recommended to cover the surface with polythene sheeting and lap all joints as soon as practicable following finishing works. Leave in position for at least 7 days. For Isocrete proprietary screeds, cure as recommended in the relevant product data sheet.

Technical Information

Appearance	Fine fibre
Base Material	Polypropylene
Fibre Length	12 mm
Fibre Thickness	18 microns
Specific Gravity	0.91
Elongation at Yield	40%
Tensile Strength	350 mPa.s (average)
Absorption	Nil
Alkali Resistance	100%

Environmental considerations

The finished system is assessed as non-hazardous to health and the environment. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

Further Information

To ensure you are specifying a fit for purpose flooring system for your project please consult our Technical Advisors on the number below or visit our website to register your interest in specifying one of the most durable floors on the market.

Flowcrete UK Ltd.
Booth Lane, Moston, Sandbach,
Cheshire, CW11 3QF. UK
Tel: +44 (0)1270 753000
Fax: +44 (0)1270 753333
Email: uk@flowcrete.com

Flowcrete Sweden AB
SE-284 80 Perstorp
Sweden
Tel: +46 435 386 30
Fax: +46 435 314 98
Email: sweden@flowcrete.com

Flowcrete International Ltd.
Lot 37631 & 37632, Jalan 6/37A,
Taman Bukit Maluri,
Industrial Area Kepong,
52100 Kuala Lumpur, Malaysia.
Tel: +60 3 6277 9575
Fax: +60 3 6277 4645
Email: malaysia@flowcrete.com

Flowcrete North America, Inc.
11133 I-45 South
Suite J, Conroe
Texas 77302
U.S.A.
Tel: +1 936 539 6700
Fax: +1 936 539 6701
Email: usa@flowcrete.com

Flowcrete
for the world at your feet